

# EASYCUT PRO301

## UNIVERSAL WATER-MISCIBLE SEMI-SYNTHETIC FLUID FOR CNC MACHINING WITH PERFECT ALUMINUM COMPATIBILITY

Water-miscible semi-synthetic concentrate of lubricating and cooling fluid. PRO301 allows for high performance machining of various aluminum alloys (incl. 2024, 6061, 6082, 7075, and others), as well as alloyed and unalloyed steels, cast iron, titanium, copper, and its alloys. Contains mineral oil.



### COMPOSITION FEATURES

- Does not contain boric acid.
- Does not contain formaldehyde.
- Contains secondary amines (DCHA).
- Contains bactericides.
- Polar lubricity improves for better aluminum performance.

### PRODUCT PROPERTIES AND ADVANTAGES

- Stable mixing of the emulsion with water hardness from 10° to 30°dH; During operation (accumulation of salts), an increase in water hardness up to 150°dH is allowed.
- High corrosion protection characteristics.
- Low foaming when using water of recommended hardness.
- Good washability (clean equipment).
- Polar lubricity improves and tight control of the in-use pH achieve optimum results when machining aluminum.

### TECHNICAL DATA

- Kinematic viscosity of the concentrate at 20°C, mm<sup>2</sup>/s — 150.
- Approximate mineral oil content, % — 30.
- pH of fresh 5% emulsion: 9,5.
- Corrosion protection DIN 51360/2 - 5% — corrosion degree 0.
- **Refractometer factor**, %/°Brix — **1.2**.

### RECOMMENDATIONS AND FEATURES

- To prepare a high-quality finely dispersed emulsion, it is recommended to use the automatic mixer device.
- For manual preparation, it is recommended to slowly add the concentrate to the water (not water to the concentrate), mixing evenly.
- The recommended concentration depends on the cutting operations and the material being processed. Turning and milling operations: 6-8% (steel, cast iron) / 7-10% (aluminum)|Grinding: 4-6%.
- The concentration of the working emulsion is measured by a manual (LQ20T) or electronic refractometer. To do this, the read value is multiplied by the **refractometer factor of 1.2**.
- EASYCUT PRO301 coolant can be used for processing of ANY aluminum and copper alloys. However, the tendency of such alloys to form spots (darkening) should be checked in advance.

### COMMENTS

Minor variations in color and appearance are possible due to the raw materials chosen. However, these have no influences on the functionality of the product.

All information on safe and proper handling can be found on the MSDS.

DESIGNED IN GERMANY

### SHELF LIFE AND STORAGE CONDITIONS

Stable for 12 months when stored at a temperature of 5 to 40 °C in unopened containers.



### COOLANT CALCULATOR

Please use our on-line coolant calculator for top-up concentration math.

Import to Canada: CNCmarket.ca Inc., 2360 Portland Street SE, Calgary, AB, T2G5S2, Canada

The technical data are representative values. All recommendations are without obligation.

We reserve the right to change the contents of this document without prior notice.